

**Preliminary Data Sheet**



# P 5046 55



- > Sensitivity: standard
- > Protective Coating: without topcoat
- > Resistance: very good stability against environmental influences
- > Archivability: 10 years\*
- > Special Features: Bisphenol A-free

Physical Properties	Value	Unit	Test Method
Base Weight	55 ± 4	g/sqm	ISO 536
	14.6 ± 1.1	lbs	17 x 22 - 500
Caliper	60 ± 5	µm	ISO 534
	2.4 ± 0.2	mil	
Smoothness (Bekk)	> 260	sec	ISO 5627
Brightness (R 457)	> 87	%	ISO 2469
Tensile Strength (MD   CD)	> 47   > 11	N/15mm	ISO 1924/2
Opacity	> 85	%	ISO 2471

Resistance	Condition	Image	Contrast
Heat	60°C / 24h	> 90	> 85
Humidity	40°C / 90% r.h. / 24h	> 90	> 90
Light incl. UV	10,000 kJ / m <sup>2</sup>	> 85	> 80
Lanolin hand cream	4h room temp.	> 65	
Ethanol (25 vol %)	dipped 20min. / 24h room temp.	> 30	
Plasticizer Tesa Document 57331	24h room temp.	> 45	
Water	dipped 20min. / 24h room temp.	> 65	

**Sensitivity**


Densitometer Technon